



180010260238



(2018)国认监认字(144)号



中国认可
国际互认
检测
TESTING
CNAS L1314

检验报告

TEST REPORT

No: WT-2020-205

产品名称: NYLON JET PRINTED CARPET

Product name

受检单位:

Inspected Body

生产单位: NANTONG HOMEDEC WEIYA

Manufacturer

CARPET CO.,LTD.

委托单位: NANTONG HOMEDEC WEIYA

Client Name

CARPET CO.,LTD.

检测类别: Entrusted Test

Test category

发布日期:

Release date

2020年07月30日

国家地毯质量监督检验中心

National Carpet Quality Supervision and Inspection Center





国家地毯质量监督检验中心
National Carpet Quality Supervision and Inspection Center
检验报告


Test Report

No: WT-2020-205


page 1 of 2

产品名称 Product name	NYLON JET PRINTED CARPET	规格型号 Specification	Width: 4 m
		商标 Trade mark	_____
委托单位 Client name	NANTONG HOMEDEC WEIYA CARPET CO.,LTD.	样品数量 Numbers of sample	m: 4×2 (1 piece)
生产单位 Manufacturer	NANTONG HOMEDEC WEIYA CARPET CO.,LTD.	电话 Client's Tel	0513-51012980 0513-51012950
受检单位 Inspected Body	_____	邮编 Postcode	_____
委托单位地址 Client's address	#16 XIN XING RD NETDA NANTONG,CHINA	抽样地点 Sampling location	_____
		抽样基数 Sampling radix	_____
样品描述 Sample description	 sample is perfect/cut pile	检测类别 Test category	Entrusted Test
		生产日期 Production date	_____
		送样人 Deliverer	Mail by the Client
送样日期 Date of submission	2020.07.01	检测日期 Date of test	2020.07.18
检测依据 Test standards	GB/T 11746-2008 《Tufted carpets》	检测项目 Test items	1、Appearance quality 2、Internal quality
检测结论 Test conclusion	The test results show that the sample(s) is(are) up to the standard by testing and evaluated as eligible products.  Date of the Issue: 2020-07-23		
备注 Remarks	All nominal values are provided by the client. The tested data are only suitable to the sample(s) received.		


批准:
Approved by



审核:
Checked by



编制:
Prepared by





国家地毯质量监督检验中心
National Carpet Quality Supervision and Inspection Center
检验报告
Test Report

No: WT-2020-205

page 2 of 2

检测项目 Test Item		单位 Unit	标准指标 Criteria	实测数值 Practical Determined Data		结果评定 Assessment	
Appearance retention: 12000 Hexapod tumbler		grade	≥ 2.0	Lengthwise	3.5	Passed	
				Widthwise	3.5		
Tuft withdrawal force		N	Cut pile ≥ 10.0	11.3		Passed	
Backing delamination strength		N	≥ 20.0	Lengthwise	54.5	Passed	
				Widthwise	26.0		
Colour fastness to light (Xennon arc)		grade	≥ 5	5		Passed	
			≥ 4 (light)	4			
Colour fastness to rubbing	dry	grade	$\geq 3-4$	Lengthwise	4-5	Passed	
				Widthwise	4-5		
	wet			Lengthwise	4-5		
				Widthwise	4-5		
Burning behavior (Level method, Tablet test)		mm	Maximum burned length ≤ 75 , at least 7 should be passed	All the 8 samples are up to standards		Passed	
Fiber type and fiber content of the carpet surface	Claimed	%	Nylon: 100	Nylon: 100		Passed	
Fiber content is nylon or wool	Minimum tolerance	%	-5	0.0			
Mass of pile per unit area above the substrate		Claimed	g/m^2	1000	995		Passed
		Tolerance	%	± 10	-0.5		
Total mass per unit area		Claimed	g/m^2	2500	2563		Passed
		Tolerance	%	± 10	2.5		
Thickness of pile above the substrate		Claimed	mm	7.0	7.1		Passed
		Tolerance	%	± 10	1.4		
Height of pile		Claimed	mm	7.5	7.5		Passed
		Tolerance	%	± 10	0.0		
Total thickness		Claimed	mm	9.5	9.6		Passed
		Tolerance	%	± 10	1.1		
Width		Claimed	m	4	3.990		Passed
		Minimum tolerance	%	-0.5	-0.2		
Appearance quality	Excellent First grade Eligible		Appearance defects	All the 10 items are up to the excellent grade		Excellent	
Remarks:							

CCSQIC/QP/009